


DOPC/CHOL Liposomes (200nm), Rhodamine DHPE labeled

Catalog: DOPC-026L

The liposomes are prepared by extrusion to 200-250nm with tight particle size distribution. The product is sterile filtered through 0.45um filters and filled in sterile vials guaranteed for 3 months shelf-life properly stored in refrigerator. Rh--DHPE is a phospholipid labeled on the head group with the red-fluorescent rhodamine B fluorophore with excitation/emission maxima ~560/580 nm.
Lipid composition: DOPC/CHOL/Rh-DHPE (54:45:1 mol/mol)
Mean particle size: 230 nm (200-250 nm, intensity weighted lognormal per DSL)
Particle size distribution: 80-100nm (half-width)

PRODUCT INFORMATION

Product Name	DOPC/CHOL Liposomes (200nm), Rhodamine DHPE labeled
Catalog Number	DOPC-026L
Product Overview	The liposomes are prepared by extrusion to 200-250nm with tight particle size distribution. The product is sterile filtered through 0.45um filters and filled in sterile vials guaranteed for 3 months shelf-life properly stored in refrigerator. Rh--DHPE is a phospholipid labeled on the head group with the red-fluorescent rhodamine B fluorophore with excitation/emission maxima ~560/580 nm. Lipid composition: DOPC/CHOL/Rh-DHPE (54:45:1 mol/mol) Mean particle size: 230 nm (200-250 nm, intensity weighted lognormal per DSL) Particle size distribution: 80-100nm (half-width)
Lipid Composition	DOPC; CHOL; Rh-DHPE
Application	Liposome production; Synthetic lipid
Storage Buffer	Hydration buffer: 10% sucrose, 20mM HEPES, pH 7.5 ± 0.2



Concentration	Lipid concentration: 50 mM (50-55 mM) Rh-DHPE: 0.5mM (0.67mg/mL)
Stability	3 Month for unopened vials, protect from light.
Storage	Store at 2-8 centigrade.
Synonyms	DOPC; 1,2-dioleoyl-sn-glycero-3-phosphocholine; CHOL; cholesterol

USAGE GUIDELINES

General Handling	Avoid excessive mixing or vortexing to prevent aggregation. Long-term storage above -80°C may result in aggregate formation. Thaw on ice before use.
Storage	Short term: +2°C to +8°C (up to 1 week) Long term: -80°C (stable for 12 months)
Stability	Stable for 12 months at -80°C. Avoid repeated freeze-thaw cycles.
Freeze / Thaw	Can be frozen, but limit to 3 freeze/thaw cycles to maintain particle integrity.

Important: This product is for **research use only**. Not intended for diagnostic or therapeutic applications. Please refer to the Safety Data Sheet (SDS) for complete handling and safety information.